

ISSN 2348 - 8034 Impact Factor- 5.070

GLOBAL JOURNAL OF ENGINEERING SCIENCE AND RESEARCHES COMPARISON OF CONVENTIONAL & DIGITAL FLEXO PLATE MAKING PROCESS FOR ACHIEVING SMALLER DOTS, HIGHER LINE COUNTS; & CONSISTENCY

(A Case study of Akriti Printers, Manesar & Truflex India, Baddi) Arohit Goyat^{*1}, Nishan Singh², Gurmeet Singh³ & Chetna Gupta⁴

*¹Associate Professor, Department of Printing Technology, GJUS&T, Hisar (Haryana)
²Assistant Professor, Department of Printing Technology, SITM, Rewari (Haryana)
³M. Tech. (Print & Graphics Communication), SITM, Rewari (Haryana)
⁴Assistant Professor, Department of Printing Technology, GJUS&T, Hisar (Haryana)

ABSTRACT

This study was carried out at Akriti Printers, Manesar & Truflex India, Baddi. Flexography is mainly used for above average quality jobs. Printing is the second largest industry of India. We are basically providing services to the society; being overlapped by various branches of Education like Computers, Electronics, Manufacturing, Chemical, Electrical, Optical and, what not? It is impossible to imagine survival of human beings without Printing. Sir Johannes Gutenberg, Father of Printing, was declared as 'Man of Millennium' by Time magazine. And, Printing is declared as the 'Greatest Invention of Millennium' again, by Time magazine. Present era is meant for the 'Survival of the Fittest'. And, this is where Printing has touched one and all.

I. INTRODUCTION

At Akriti Printers, Manesar&Truflex India, Baddi, this study was conducted. This study is to analysis Flexo plate making process and compares the conventional and digital plate making process in conventional and Digital press houses

II. RESEARCH OBJECTIVE

The objective of this study is to analysis Flexo plate making process and compares the conventional and digital plate making process in conventional and Digital press houses.

III. RESEARCH METHODOLOGY

The whole study has been divided in 3 sub parts with complete understanding of flexographic plate making process along with the cost, efficiency, consumption of time in conventional and digital plate making process and advantage of digital flexographic plates.

The following methodology was adopted during the study.

- 1. Study of conventional plate making process, equipment and materials.
- 2. Study of Digital plate making process, equipment and materials.
- 3. Comparison between conventional Flexoand Digital plate making process.

IV. DATA COLLECTION

CONVENTIONAL FLEXO PLATE MAKING PROCESS AT TRUFLEX INDIA, BADDI

Profile of Organization

Truflex India is flexographic prepress trade shop, working with its expertise to provide stronger "value added" service to the printing industry.





ISSN 2348 - 8034 Impact Factor- 5.070

Truflex India as trade shop provides flexo and letterpress plates to various print converters.

- Lamitube Printer
- Corrugation Printer
- Offset Printer
- PP Bags Printer

DETAILS OF EQUIPMENT'S AND MATERIAL USED AT TRUFLEX INDIA (CONVENTIONAL FLEXO PREPRESS HOUSE)

Equipments

- Agfa Avantra 20-25 OLP (Image Setter)
- D Graph 2530, Inglese All in One, (Water washable plate exposure, washer, dryer)
- Tower type 2530, AGI-6RL- All in One (Solvent washable plate exposure, washer, dryer)

Materials

- Fujifilm Benefit(Imaging Film) Roll of different Size -12", 14", 16", 18"
- Fujifilm Processing Chemical Benefit D1 & F1– Developer, Fixer (5 Ltr. Can)
- Conventional/Analog Flexo Plates (Solvent Wash) Company DuPont(Cyrel) Plate thickness 2.84 mm, 3.9 mm, 4.7 mm
- Conventional Letterpress Plates (Water wash) Company- Toray (DG 95) Toyobo MC, GC Plate thickness- 0.95mm
- Flexo Plate processing chemicals Perclow(PCE) &Butanol (NBA)

CONVENTIONAL LETTERPRESS PLATE MAKING PROCESS & PARAMETERS

Main Exposure time (Front)	-	90 sec
Back Exposure time	-	120 sec
Washing time	-	90 sec
Drying Time	-	20 min @ 75 Degree C
Post Exposure time	-	90 sec

Conventional Flexo plate making process & Parameters

1	01	
Back Exposure time	-	1 min 40 sec
Main Exposure time	-	15 min
Washing time 5 min	-	6 min (Clock wise)
Drying time	-	90 min
Post Exp. (Front) time	-	5 min
Curing time (UV-C)	-	6 min

CONVENTIONALFLEXO/LETTERPRESSPLATEMAKINGDETAILS

Sr. No	Name ofJobs	Dates	Plate Used	Plate Quality Issue	Wastageof Plate
1.	Burno	22/1/18	Toray	No	No
2	Henna	23/1/18	Toray	No	No
3	Fair Soft	24/1/18	Тоуоbo	yes	Remake due to Dot issue
4	Cosmo	29/1/18	Toray	No	No






ISSN 2348 - 8034 Impact Factor- 5.070

10.5	201/2cm0u0.252072				impact ractor 5.
5	Herbal Toothpaste	30/1/18	Toyobo	No	No
6	Fastgel	2/2/18	Toyobo	No	No
7	Pain Relief	5/2/18	Тоуоbo	No	No
8	XpGel	6/2/18	Toray	yes	Remake due to Dot issue
9	Glow pack	8/2/18	Toray	No	No
10	Fresh	12/2/18	Toyobo	No	No
11	Betasol	15/2/18	Toray	No	No
12	I-Gurad	19/2/18	Toray	No	No
13	FFglow	20/2/18	Toray	yes	Color correction
14	Sensitive	23/2/18	Тоуово	No	No
15	Act-fast	27/2/18	Toray	No	No

DIGITAL FLEXO PLATE



V. RESULT&DISCUSSION

We analyzed the plate cost, processing cost and difference between qualities of both plates which will help the Flexography printer to improve their printing qualities and increase efficiencies of Printing machine.

Digital vs. Conventional

- 1. More open reverses
- Conventional limited to8pt negative text




288



- Digital easily keeps 2pt negative text open
- 2. Smaller minimum dot
- Conventional minimum dot: 6%
- Digital minimum dot: 1%
- 3. Higher line-counts
- Conventional limited to85 lpi
- Digital up to 133 lpi possible
- 4. Consistency& Repeatability
- Conventional: contact problems during UV-Exposure +chemistry effects
- Digital: standardization by highest consistency and repeatability

Benefits of digital flexo plates




289




ISSN 2348 - 8034 Impact Factor- 5.070



ISSN 2348 - 8034 Impact Factor- 5.070






290

- Print quality improvement
- Higher dot definition
- More open reverses
- Finer print Details
- Extended tonal Range
- Digital Flexo is the only solution for extended tonal range.
- All film based quality improvements Always lead into trade-offs







ISSN 2348 - 8034 Impact Factor- 5.070

Benefits of digital flexo plates (MoneySaving)

About 18% generals avings inplate making department

- No film storage
- No solvents
- Less handling steps
- Less errors due to digital data

• Faster throughput

Higher press utilization


- Higher print quality possible
- Faster press setup due to high plate quality and high plate consistency(10-15%)
- Less spoilage (10 20%)
- Higher runs lengths (at same quality like conventional plates)
- Due to better shaped dots
- Longer cleaning intervals
- Due to better shaped dots



291



ISSN 2348 - 8034 Impact Factor- 5.070



REFERENCES

- <u>https://www.thoughtco.com/flexography-printing-technique-1074610</u>
- <u>http://pneac.org/vfp/prepress-traditional-prepress-platemaking</u>
- <u>http://pneac.org/vfp/prepress-traditional-prepress</u>
- <u>http://pneac.org/vfp/prepress-digital-platemaking</u>
- Flexographic printing element having an ireablatable layer and process for making a flexographic printing plate, BY ROXY N. FAN
- Process for making a flexographic printing plate, By-Carol M. Van Zoeren
- Flexographic printing plate process, By-John A. Martens
- Method for process less flexographic printing and flexographic printing plate, By- Daniel Gelbart
- Device for forming flexographic printing plate, By-<u>John A. Peterson</u>, <u>Kurt F. F. Feil</u>, <u>Craig D. Lien</u>, <u>John</u> <u>A. Martens</u>, <u>Gary A. Staus</u>, <u>Gary D. VanDerWerff</u>
- Process for making a flexographic printing plate and a photosensitive element for use in the process, BY-<u>Roxy Ni Fan, Mark A. Hackler, Anandkumar R. Kannurpatti</u>,
- Apparatus for automatically processing photopolymer plates, By ShozoTsuchida, SakuoOkai
- Laser engravable single-layer flexographic printing element, By <u>Stephen Cushner</u>, <u>Roxy Ni Fan</u>, <u>Ernst</u> <u>Leberzammer</u>, <u>Paul Thomas Shea</u>, <u>Carol Marie Van Zoeren</u>
- Flexographic printing plate, By- Carol Marie Van Zoeren
- Flexographic printing plate with mask layer and methods of imaging and printing, By <u>Charles D. DeBoer</u>, <u>Mitchell S. Burberry</u>.

